

FIELD EMISSION DISPLAY WITH SMOOTH ALUMINUM FILM

Abstract of the Disclosure

This invention provides a conductive aluminum film and method of forming the same, wherein a non-conductive impurity is incorporated into the aluminum film. In one embodiment, the introduction of nitrogen creates an aluminum nitride subphase which pins down hillocks in the aluminum film to maintain a substantially smooth surface. The film remains substantially hillock-free even after subsequent thermal processing. The aluminum nitride subphase causes only a nominal increase in resistivity (resistivities remain below about 12 $\mu\Omega\text{-cm}$), thereby making the film suitable as an electrically conductive layer for integrated circuit or display devices.

[SHL-1252.4:020399]
O:\DOCS\LJMLJM-1166.DOC
012802

10060342 012802